

FORM PTO-1390 (Modified)
(REV 11-98)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

00537-181002

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/744350

INTERNATIONAL APPLICATION NO.
PCT/US99/14869 ✓INTERNATIONAL FILING DATE
July 9, 1999 ✓PRIORITY DATE CLAIMED
July 23, 1998 ✓

TITLE OF INVENTION

ENCAPSULATION OF WATER SOLUBLE PEPTIDES ✓

APPLICANT(S) FOR DO/EO/US

IGNATIUS, Francis, X. ✓

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☒ Certificate of Mailing by Express Mail
20. ☐ Other items or information:

"Express Mail" mailing label number E1 2664362 64 US
Date of Deposit 1/23/01

I hereby certify that this paper or form is transmitted with
the United States Postal Service to the Office to
Addressee" service under 37 CFR 1.101, at the date indicated above
and is addressed to the Assistant Commissioner for Patents,
Washington D.C. 20503

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.53) 09/744350		INTERNATIONAL APPLICATION NO. PCT/US99/14869		ATTORNEY'S DOCKET NUMBER 00537-181002	
--	--	--	--	---	--

21. The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO **\$1,000.00**
- ☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO **\$860.00**
- ☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO **\$710.00**
- ☐ International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) **\$690.00**
- ☐ International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) **\$100.00**

ENTER APPROPRIATE BASIC FEE AMOUNT =

CALCULATIONS PTO USE ONLY

Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).				\$0.00	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	48 - 20 =	28	x \$18.00	\$504.00	
Independent claims	3 - 3 =	0	x \$80.00	\$0.00	
Multiple Dependent Claims (check if applicable). <input type="checkbox"/>				\$0.00	
TOTAL OF ABOVE CALCULATIONS =				\$1,364.00	
Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable). <input type="checkbox"/>				\$0.00	
SUBTOTAL =				\$1,364.00	
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492 (f)).				\$0.00	
TOTAL NATIONAL FEE =				\$1,364.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). <input type="checkbox"/>				\$0.00	
TOTAL FEES ENCLOSED =				\$1,364.00	
				Amount to be: refunded	\$
				charged	\$

☒ A check in the amount of **\$1,364.00** to cover the above fees is enclosed.

☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees.
 A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **06-1050** A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Y. Rocky Tsao
Fish & Richardson P.C.
225 Franklin Street
Boston , MA 02110-2804

SIGNATURE

Y. Rocky Tsao
 NAME

34, 053
 REGISTRATION NUMBER

January 23, 2001
 DATE

ENCAPSULATION OF WATER SOLUBLE PEPTIDES

5

Background of the Invention

This invention relates to a process for preparing biodegradable microspheres and or nanospheres using an oil-in-water process, which microspheres and nanospheres can be used for the controlled release of bioactive peptides.

10

A variety of techniques are described in the literature for the preparation of polymer microspheres for the sustained release of bioactive peptides. Among the different techniques such as spray drying, spray congealing, coacervation, solvent evaporation etc., solvent evaporation is simplest to scale-up industrially (for a recent review see protein delivery from biodegradable microspheres, by J.L. Cleland in Protein Delivery edited by L. Sanders and W. Hendren, Plenum Press, NY 1997). Solvent evaporation is usually practiced by dissolving or suspending an active ingredient in a polymer solution, which is further dispersed in the form of droplets in a suitable medium containing surfactants capable of stabilizing the droplets, and the polymer droplets are hardened by evaporation of the solvent. When the polymer is dissolved in an organic medium and then emulsified in water, the process is called oil-in-water process (O/W). Water soluble peptides cannot be encapsulated by the O/W process, due to the partition of the water soluble peptides into the aqueous medium, resulting in low encapsulation efficiency. Higher encapsulation efficiencies were achieved by a more complex double emulsion water-in-oil-in-water (W/O/W) process (US Patent No. 5,271,945) or by using an oil-in-oil (O/O) process (EP 0330180 B1). The main drawback of the latter process is the use of different organic solvents, first to solubilize the polymer, and then to wash the polymer microspheres free of the oil in which they are formed. Therefore, the simple O/W emulsion solvent evaporation process is the most attractive, provided higher encapsulation efficiency can be achieved, since only one organic solvent is involved, and the residual organic solvent can be removed by vacuum drying.

30

The main hurdle to achieving higher encapsulation efficiency of the peptides is their water solubility. Solubility of peptides depends on the nature of

the counter-ion. The aqueous solubility of a peptide is considerably reduced when the peptide is present as a free base, due to intermolecular interactions. One method of enhancing the encapsulation efficiency of the peptides in an O/W process according to the present invention, is by using a peptide as a free base

5 adsorbed onto a bioresorbable inorganic matrix, such as hydroxyapatite, Calcium monohydrogen phosphate, zinc hydroxide, alum etc. In the case of encapsulation of LHRH agonists such as tryptorelin, leuprolin, goserlin, busreltin, etc., the presence of calcium phosphate in the microspheres may not only serve to stabilize the neutralized peptide but also act as a calcium supplement, since

10 one of the biggest concerns of continuous therapy using LHRH agonists is loss of bone density. This method of encapsulation is most suited when the peptide loading in excess of 5-6% is not desired. In the case of high peptide loading, a heterogeneous distribution of the drug particles, even if they were stabilized by adsorption onto a solid matrix or not, inside the microspheres leads to non-

15 predictable release profiles.

In cases where higher drug loading as well as predictable release profiles are desired, a second method of reducing the aqueous solubility of the drug, without sacrificing its potency, is by simply forming reversible water insoluble salts of mono-functional or multi-functional detergents and/or polymers

20 or a combination of both, as exemplified by Schally et al. in US Patent No. 4,010,125. The aqueous solubility of the peptides can be considerably reduced by forming salts of mono-functional detergents such as sodium dodecyl sulfate, or of multi-functional anionic species such as pamoate, tannate, alginate, carboxymethyl cellulose, leading to the precipitation of the water insoluble

25 peptide salt. Among the water insoluble salts, some exhibit good solubility in common organic solvents. U.S. Patent No. 5,672,659 describes compositions formed between anionic carboxylate functionalized polyesters and cationic peptides. These compositions as well as those formed with certain anionic detergents such as dioctylsulfosuccinate are found to exhibit good solubility in

30 organic solvents such as dichloromethane (DCM), chloroform, acetonitrile, ethyl acetate, and the like.

During the water based encapsulation of the peptide, either as a free base adsorbed on to solid matrix or as water insoluble but organic solvent

soluble salt, the pH of the aqueous medium can dramatically increase the water solubility, by affecting the equilibrium between the complexed and uncomplexed state. If the pH is not maintained at 7 the equilibrium may shift, favoring the solubilization of the peptide, leading to poor encapsulation efficiency.

5 It is therefore the object of the present invention to provide polymer microspheres and/or nanospheres prepared by a simple O/W method, where the encapsulation efficiency achieved can be greater than 85%.

Summary of the invention

In one aspect, the present invention is directed to process A, which is a process for preparing polymer microspheres comprising a polymer and a peptide, which comprises the steps of:

neutralizing a peptide salt with a weak base in an aqueous medium wherein said medium comprises a suspension of hydroxyapatite or a solution of calcium mono-hydrogen phosphate to form a precipitate;

15 isolating the precipitate;

suspending the precipitate in an organic solvent, which comprises a polymer dissolved therein to form a suspension;

dispersing the suspension in an aqueous solution of a surfactant; and evaporating the organic solvent to isolate the polymer microspheres.

20 A preferred process of process A, comprises the additional step of dissolving the peptide salt in a minimum of water before neutralizing the peptide salt.

In a second aspect, the present invention is directed to process B, which is a process for preparing polymer microspheres and nanospheres comprising a polymer and a peptide, which comprises the steps of:

dissolving a salt of a peptide complexed with an anionically or cationically functionalized biodegradable polyester in an organic solvent to form a solution;

dispersing the solution in an aqueous solution of a surfactant; and

evaporating the organic solvent to isolate the polymer microspheres and nanospheres.

30 A preferred process of process B is where the anionically functionalized biodegradable polyester is functionalized with an anionic moiety selected from the group consisting of carboxylate, phosphate and sulfate and the cationically

functionalized biodegradable polyester is functionalized with a cationic moiety selected from the group consisting of amino, amidino, guadino, ammonium, cyclic amino groups and nucleic acid bases.

In a third aspect, the present invention is directed to a process for
5 preparing polymer microspheres and nanospheres comprising a polymer and a peptide, which comprises the steps of:

dissolving a salt of a peptide complexed with an anionic counterion in an organic solvent which is selected from the group consisting of dichloromethane, chloroform and ethyl acetate to form a solution;

10 dispersing the solution in a surfactant; and

evaporating the organic solvent to isolate the polymer microspheres and nanospheres.

A preferred process of any of the foregoing processes is where the surfactant is one or more of sodium oleate, sodium stearate, sodium
15 laurylsulphate, a poly(oxyethylene) sorbitan fatty acid ester, polyvinylpyrrolidone, polyvinyl alcohol, carboxymethyl cellulose, lecithin, gelatin or hyaluronic acid.

A preferred process of any of the foregoing processes is where the surfactant is polyvinyl alcohol and the pH of the polyvinyl alcohol is 6.5-7.5.

A preferred process of any of the foregoing processes is where the pH of
20 the polyvinyl alcohol is 6.9-7.1.

A preferred process of any of the foregoing processes is where the organic solvent is dichloromethane, chloroform or ethyl acetate.

A preferred process of any of the foregoing processes is where the organic solvent is dichloromethane and the concentration of the polymer in
25 dichloromethane is 0.5% to 30% by weight.


A preferred process of any of the foregoing processes is where the concentration of the polymer in dichloromethane is 0.5% to 10% by weight.

A preferred process of any of the foregoing processes is where the peptide is growth hormone releasing peptide, luteinizing hormone-releasing
30 hormone, somatostatin, bombesin, gastrin releasing peptide, calcitonin, bradykinin, galanin, melanocyte stimulating hormone, growth hormone releasing factor, amylin, tachykinins, secretin, parathyroid hormone, enkephalin, endothelin, calcitonin gene releasing peptide, neuromedins, parathyroid


hormone related protein, glucagon, neurotensin, adrenocorticotrophic hormone, peptide YY, glucagon releasing peptide, vasoactive intestinal peptide, pituitary adenylate cyclase activating peptide, motilin, substance P, neuropeptide Y, or TSH or an analogue or a fragment thereof or a pharmaceutically acceptable salt thereof.

A preferred process of any of the foregoing processes is where the peptide is the LHRH analogue of the formula pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂.

A preferred process of any of the foregoing processes is where the peptide is selected from the group of somatostatin analogues consisting of H-D-β-Nal-Cys-Tyr-D-Trp-Lys-Thr-Cys-Thr-NH₂,



, and




15 .


A preferred process of any of the foregoing processes is where the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

In another aspect, the present invention is directed to a polymer microsphere made according to process A, process B or process C.

Preferred of the immediately foregoing process is where the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof and where the peptide is the LHRH analogue of the formula pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂ or the peptide is selected from the group of somatostatin analogues consisting of H-D-β-Nal-Cys-Tyr-D-Trp-Lys-Thr-Cys-Thr-NH₂,



, and



Detailed Description of the Invention

The terms biodegradable and bioerodable are used interchangeably and
 5 is intended to mean that the material is degraded in the biological environment
 of the subject that to which it is administered.

Polymer microspheres made according to a process of this invention can
 be administered by intramuscular (IM), subcutaneous, pulmonary or oral route.
 Polymer nanospheres made according to a process of this invention in addition
 10 to being deliverable in the same manner as disclosed for microspheres can also
 be administered via inhalation methods such as those discussed in *Pulmonary
 Drug Delivery*, J. Yu and Y.W. Chien in *Critical Reviews™* in Therapeutic Drug
 Carrier Systems, 14(4): 395-453, (1997), the contents of which are incorporated
 herein by reference. The microspheres and nanospheres made according to a
 15 process of this invention contain from less than 0.1% by weight up to
 approximately 50% by weight of a peptide. The polymer microspheres
 containing a peptide are prepared by an O/W emulsion solvent evaporation
 process, without compromising the much desired high encapsulation efficiency.
 Encapsulation efficiencies greater than 85% can be achieved according to the
 20 teachings of the present invention.

Polymers that can be used to form microspheres include bioerodible
 polymers such as polyesters (ex. polylactides, polyglycolides, polycaprolactone
 and copolymers and blends thereof), polycarbonates, polyorthoesters,
 polyacetals, polyanhydrides, their copolymers or blends, and non-bioerodible
 25 polymers such as polyacrylates, polystyrenes, polyvinylacetates, etc. Both types
 of polymers may optionally contain anionic or cationic groups. In general a
 polymer solution can be prepared containing between 1% and 20% polymer,
 preferably between 5% and 15% polymer. The polymer solution can be
 prepared in dichloromethane (DCM), chloroform, ethylacetate, methylformate,
 30 dichloroethane, toluene, cyclohexane and the like.

Any peptide can be incorporated in the microspheres of this invention. Examples of peptides that can be incorporated in the microspheres produced by a process of this invention are growth hormone releasing peptide (GHRP), luteinizing hormone-releasing hormone (LHRH), somatostatin, bombesin, gastrin releasing peptide (GRP), calcitonin, bradykinin, galanin, melanocyte stimulating hormone (MSH), growth hormone releasing factor (GRF), amylin, tachykinins, secretin, parathyroid hormone (PTH), enkephalin, endothelin, calcitonin gene releasing peptide (CGRP), neuromedins, parathyroid hormone related protein (PTHrP), glucagon, neurotensin, adrenocorticotrophic hormone (ACTH), peptide YY (PYY), glucagon releasing peptide (GLP), vasoactive intestinal peptide (VIP), pituitary adenylate cyclase activating peptide (PACAP), motilin, substance P, neuropeptide Y (NPY), TSH and analogs and fragments thereof or a pharmaceutically acceptable salt thereof.

The term "peptide" is intended to include peptide, polypeptides and proteins.

Examples of specific LHRH analogues that can be incorporated in the microspheres of this invention are tryptorelin (p-Glu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂), buserelin ([D-Ser(t-Bu)⁶, des-Gly-NH₂¹⁰]-LHRH(1-9)NH₂), deslorelin ([D-Trp⁶, des-Gly-NH₂¹⁰]-LHRH(1-9)NH₂), fertirelin ([des-Gly-NH₂¹⁰]-LHRH(1-9)NH₂), gosrelin ([D-Ser(t-Bu)⁶, Azgly¹⁰]-LHRH), histrelin ([D-His(Bzl)⁶, des-Gly-NH₂¹⁰]-LHRH(1-9)NH₂), leuprorelin ([D-Leu⁶, des-Gly-NH₂¹⁰]-LHRH(1-9)NH₂), lutrelin ([D-Trp⁶, MeLeu⁷, des-Gly-NH₂¹⁰]-LHRH(1-9)NH₂), nafarelin ([D-Nal⁶]-LHRH and pharmaceutically acceptable salts thereof.

Preferred somatostatin analogs that can be incorporated in the microspheres and/or nanospheres of this invention are those covered by formulae or those specifically recited in the publications set forth below, all of which are hereby incorporated by reference:

Van Binst, G. et al. Peptide Research 5:8 (1992);

Horvath, A. et al. Abstract, "Conformations of Somatostatin Analogs Having Antitumor Activity", 22nd European peptide Symposium, September 13-19, 1992, Interlaken, Switzerland;

PCT Application WO 91/09056 (1991);

EP Application 0 363 589 A2 (1990);

- U.S. Patent No. 4,904,642 (1990);
U.S. Patent No. 4,871,717 (1989);
U.S. Patent No. 4,853,371 (1989);
U.S. Patent No. 4,725,577 (1988);
5 U.S. Patent No. 4,684,620 (1987)
U.S. Patent No. 4,650,787 (1987);
U.S. Patent No. 4,603,120 (1986);
U.S. Patent No. 4,585,755 (1986);
EP Application 0 203 031 A2 (1986);
10 U.S. Patent No. 4,522,813 (1985);
U.S. Patent No. 4,486,415 (1984);
U.S. Patent No. 4,485,101 (1984);
U.S. Patent No. 4,435,385 (1984);
U.S. Patent No. 4,395,403 (1983);
15 U.S. Patent No. 4,369,179 (1983);
U.S. Patent No. 4,360,516 (1982);
U.S. Patent No. 4,358,439 (1982);
U.S. Patent No. 4,328,214 (1982);
U.S. Patent No. 4,316,890 (1982);
20 U.S. Patent No. 4,310,518 (1982);
U.S. Patent No. 4,291,022 (1981);
U.S. Patent No. 4,238,481 (1980);
U.S. Patent No. 4,235,886 (1980);
U.S. Patent No. 4,224,190 (1980);
25 U.S. Patent No. 4,211,693 (1980);
U.S. Patent No. 4,190,648 (1980);
U.S. Patent No. 4,146,612 (1979);
U.S. Patent No. 4,133,782 (1979);
U.S. Patent No. 5,506,339 (1996);
30 U.S. Patent No. 4,261,885 (1981);
U.S. Patent No. 4,728,638 (1988);
U.S. Patent No. 4,282,143 (1981);
U.S. Patent No. 4,215,039 (1980);

- U.S. Patent No. 4,209,426 (1980);
U.S. Patent No. 4,190,575 (1980);
EP Patent No. 0 389 180 (1990);
EP Application No. 0 505 680 (1982);
5 EP Application No. 0 083 305 (1982);
EP Application No. 0 030 920 (1980);
PCT Application No. WO 88/05052 (1988);
PCT Application No. WO 90/12811 (1990);
PCT Application No. WO 97/01579 (1997);
10 PCT Application No. WO 91/18016 (1991);
U.K. Application No. GB 2,095,261 (1981); and
French Application No. FR 2,522,655 (1983).

- Examples of somatostatin analogs include, but are not limited to, the
following somatostatin analogs which are disclosed in the above-cited
15 references:

- H-D- β -Nal-Cys-Tyr-D-Trp-Lys-Thr-Cys-Thr-NH₂;
H-D-Phe-Cys-Phe-D-Trp-Lys-Thr-Cys- β -Nal-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Thr-Cys- β -Nal-NH₂;
H-D- β -Nal-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
20 H-D-Phe-Cys-Tyr-D-Trp-Lys-Thr-Pen-Thr-NH₂;
H-D-Phe-Cys-Phe-D-Trp-Lys-Thr-Pen-Thr-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Thr-Pen-Thr-OH;
H-D-Phe-Cys-Phe-D-Trp-Lys-Thr-Pen-Thr-OH;
H-Gly-Pen-Phe-D-Trp-Lys-Thr-Cys-Thr-OH;
25 H-Phe-Pen-Tyr-D-Trp-Lys-Thr-Cys-Thr-OH;
H-Phe-Pen-Phe-D-Trp-Lys-Thr-Pen-Thr-OH;
H-D-Phe-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-ol;
H-D-Phe-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
H-D-Trp-Cys-Tyr-D-Trp-Lys-Val-Cys-Thr-NH₂;
30 H-D-Trp-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Val-Cys-Thr-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Val-Cys-Trp-NH₂;


- H-D-Phe-Cys-Tyr-D-Trp-Lys-Val-Cys-Thr-NH₂;
Ac-D-Phe-Lys*-Tyr-D-Trp-Lys-Val-Asp*-Thr-NH₂ (an amide bridge formed
between Lys* and Asp*);
Ac-hArg(Et)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
5 Ac-D-hArg(Et)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(Bu)-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(Et)₂-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-L-hArg(Et)₂-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(CH₂CF₃)₂-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
10 Ac-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Phe-NH₂;
Ac-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NHEt;
Ac-L-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys(Me)-Thr-Cys-Thr-NH₂;
15 Ac-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys(Me)-Thr-Cys-Thr-NHEt;
Ac-hArg(CH₃, hexyl)-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
H-hArg(hexyl)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(Et)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NHEt;
Ac-D-hArg(Et)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Phe-NH₂;
20 Propionyl-D-hArg(Et)₂-Gly-Cys-Phe-D-Trp-Lys(iPr)-Thr-Cys-Thr-NH₂;
Ac-D-β-Nal-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Gly-hArg(Et)₂-NH₂;
Ac-D-Lys(iPr)-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-D-hArg(CH₂CF₃)₂-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-
NH₂;
25 Ac-D-hArg(CH₂CF₃)₂-D-hArg(CH₂CF₃)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Phe-
NH₂;
Ac-D-hArg(Et)₂-D-hArg(Et)₂-Gly-Cys-Phe-D-Trp-Lys-Thr-Cys-Thr-NH₂;
Ac-Cys-Lys-Asn-4-Cl-Phe-Phe-D-Trp-Lys-Thr-Phe-Thr-Ser-D-Cys-NH₂;
H-Bmp-Tyr-D-Trp-Lys-Val-Cys-Thr-NH₂;
30 H-Bmp-Tyr-D-Trp-Lys-Val-Cys-Phe-NH₂;
H-Bmp-Tyr-D-Trp-Lys-Val-Cys-p-Cl-Phe-NH₂;
H-Bmp-Tyr-D-Trp-Lys-Val-Cys-β-Nal-NH₂;

- H-D- β -Nal-Cys-Tyr-D-Trp-Lys-Val-Cys-Thr-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Abu-Cys-Thr-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Abu-Cys- β -Nal-NH₂;
H-pentafluoro-D-Phe-Cys-Tyr-D-Trp-Lys-Val-Cys-Thr-NH₂;
5 Ac-D- β -Nal-Cys-pentafluoro-Phe-D-Trp-Lys-Val-Cys-Thr-NH₂;
H-D- β -Nal-Cys-Tyr-D-Trp-Lys-Val-Cys- β -Nal-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Val-Cys- β -Nal-NH₂;
H-D- β -Nal-Cys-Tyr-D-Trp-Lys-Abu-Cys-Thr-NH₂;
H-D-p-Cl-Phe-Cys-Tyr-D-Trp-Lys-Abu-Cys-Thr-NH₂;
10 Ac-D-p-Cl-Phe-Cys-Tyr-D-Trp-Lys-Abu-Cys-Thr-NH₂;
H-D-Phe-Cys- β -Nal-D-Trp-Lys-Val-Cys-Thr-NH₂;
H-D-Phe-Cys-Tyr-D-Trp-Lys-Cys-Thr-NH₂;
cyclo(Pro-Phe-D-Trp-N-Me-Lys-Thr-Phe);
cyclo(Pro-Phe-D-Trp-N-Me-Lys-Thr-Phe);
15 cyclo(Pro-Phe-D-Trp-Lys-Thr-N-Me-Phe);
cyclo(N-Me-Ala-Tyr-D-Trp-Lys-Thr-Phe);
cyclo(Pro-Tyr-D-Trp-Lys-Thr-Phe);
cyclo(Pro-Phe-D-Trp-Lys-Thr-Phe);
cyclo(Pro-Phe-L-Trp-Lys-Thr-Phe);
20 cyclo(Pro-Phe-D-Trp(F)-Lys-Thr-Phe);
cyclo(Pro-Phe-Trp(F)-Lys-Thr-Phe);
cyclo(Pro-Phe-D-Trp-Lys-Ser-Phe);
cyclo(Pro-Phe-D-Trp-Lys-Thr-p-Cl-Phe);
cyclo(D-Ala-N-Me-D-Phe-D-Thr-D-Lys-Trp-D-Phe);
25 cyclo(D-Ala-N-Me-D-Phe-D-Val-Lys-D-Trp-D-Phe);
cyclo(D-Ala-N-Me-D-Phe-D-Thr-Lys-D-Trp-D-Phe);
cyclo(D-Abu-N-Me-D-Phe-D-Val-Lys-D-Trp-D-Tyr);
cyclo(Pro-Tyr-D-Trp-t-4-AchxAla-Thr-Phe);
cyclo(Pro-Phe-D-Trp-t-4-AchxAla-Thr-Phe);
30 cyclo(N-Me-Ala-Tyr-D-Trp-Lys-Val-Phe);
cyclo(N-Me-Ala-Tyr-D-Trp-t-4-AchxAla-Thr-Phe);
cyclo(Pro-Tyr-D-Trp-4-Amphe-Thr-Phe);

- cyclo(Pro-Phe-D-Trp-4-Amphe-Thr-Phe);
cyclo(N-Me-Ala-Tyr-D-Trp-4-Amphe-Thr-Phe);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Gaba);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Gaba-Gaba);
5 cyclo(Asn-Phe-D-Trp-Lys-Thr-Phe);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-NH(CH₂)₄CO);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-β-Ala);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-D-Glu)-OH;
cyclo(Phe-Phe-D-Trp-Lys-Thr-Phe);
10 cyclo(Phe-Phe-D-Trp-Lys-Thr-Phe-Gly);
cyclo(Phe-Phe-D-Trp-Lys-Thr-Phe-Gaba);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Gly);
cyclo(Asn-Phe-Phe-D-Trp(F)-Lys-Thr-Phe-Gaba);
cyclo(Asn-Phe-Phe-D-Trp(NO₂)-Lys-Thr-Phe-Gaba);
15 cyclo(Asn-Phe-Phe-Trp(Br)-Lys-Thr-Phe-Gaba);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Phe(I)-Gaba);
cyclo(Asn-Phe-Phe-D-Trp-Lys-Thr-Tyr(But)-Gaba);
cyclo(Bmp-Lys-Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Thr-Pro-Cys)-OH;
cyclo(Bmp-Lys-Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Thr-Pro-Cys)-OH;
20 cyclo(Bmp-Lys-Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Thr-Tpo-Cys)-OH;
cyclo(Bmp-Lys-Asn-Phe-Phe-D-Trp-Lys-Thr-Phe-Thr-MeLeu-Cys)-OH;
cyclo(Phe-Phe-D-Trp-Lys-Thr-Phe-Phe-Gaba);
cyclo(Phe-Phe-D-Trp-Lys-Thr-Phe-D-Phe-Gaba);
cyclo(Phe-Phe-D-Trp(5F)-Lys-Thr-Phe-Phe-Gaba);
25 cyclo(Asn-Phe-Phe-D-Trp-Lys(Ac)-Thr-Phe-NH-(CH₂)₃-CO);
cyclo(Lys-Phe-Phe-D-Trp-Lys-Thr-Phe-Gaba);
cyclo(Lys-Phe-Phe-D-Trp-Lys-Thr-Phe-Gaba);
cyclo(Orn-Phe-Phe-D-Trp-Lys-Thr-Phe-Gaba);
H-Cys-Phe-Phe-D-Trp-Lys-Thr-Phe-Cys-NH₂;
30 H-Cys-Phe-Phe-D-Trp-Lys-Ser-Phe-Cys-NH₂;
H-Cys-Phe-Tyr-D-Trp-Lys-Thr-Phe-Cys-NH₂; and
H-Cys-Phe-Tyr(I)-D-Trp-Lys-Thr-Phe-Cys-NH₂.

A disulfide bridge is formed between the two free thiols (e.g., Cys, Pen, or Bmp residues) when they are present in a peptide; however, the disulfide bond is not shown.

Also included are somatostatin agonists of the following formula:



10 wherein

A^1 is a D- or L- isomer of Ala, Leu, Ile, Val, Nle, Thr, Ser, β -Nal, β -Pal, Trp, Phe, 2,4-dichloro-Phe, pentafluoro-Phe, p-X-Phe, or o-X-Phe, wherein X is CH_3 , Cl, Br, F, OH, OCH_3 or NO_2 ;

A^2 is Ala, Leu, Ile, Val, Nle, Phe, β -Nal, pyridyl-Ala, Trp, 2,4-dichloro-Phe, 15 pentafluoro-Phe, o-X-Phe, or p-X-Phe, wherein X is CH_3 , Cl, Br, F, OH, OCH_3 or NO_2 ;

A^3 is pyridyl-Ala, Trp, Phe, β -Nal, 2,4-dichloro-Phe, pentafluoro-Phe, o-X-Phe, or p-X-Phe, wherein X is CH_3 , Cl, Br, F, OH, OCH_3 or NO_2 ;

A^6 is Val, Ala, Leu, Ile, Nle, Thr, Abu, or Ser;

20 A^7 is Ala, Leu, Ile, Val, Nle, Phe, β -Nal, pyridyl-Ala, Trp, 2,4-dichloro-Phe, pentafluoro-Phe, o-X-Phe, or p-X-Phe, wherein X is CH_3 , Cl, Br, F, OH, OCH_3 or NO_2 ;

A^8 is a D- or L-isomer of Ala, Leu, Ile, Val, Nle, Thr, Ser, Phe, β -Nal, pyridyl-Ala, Trp, 2,4-dichloro-Phe, pentafluoro-Phe, p-X-Phe, or o-X-Phe, 25 wherein X is CH_3 , Cl, Br, F, OH, OCH_3 or NO_2 ;

each R_1 and R_2 , independently, is H, lower acyl or lower alkyl; and R_3 is OH or NH_2 ; provided that at least one of A^1 and A^8 and one of A^2 and A^7 must be an aromatic amino acid; and further provided that A^1 , A^2 , A^7 and A^8 cannot all be aromatic amino acids.

30 Examples of linear agonists to be used in a process of this invention include:


H-D-Phe-p-chloro-Phe-Tyr-D-Trp-Lys-Thr-Phe-Thr- NH_2 ;

H-D-Phe-p- NO_2 -Phe-Tyr-D-Trp-Lys-Val-Phe-Thr- NH_2 ;


H-D-Nal-p-chloro-Phe-Tyr-D-Trp-Lys-Val-Phe-Thr- NH_2 ;

H-D-Phe-Phe-Phe-D-Trp-Lys-Thr-Phe-Thr-NH₂;
 H-D-Phe-Phe-Tyr-D-Trp-Lys-Val-Phe-Thr-NH₂;
 H-D-Phe-p-chloro-Phe-Tyr-D-Trp-Lys-Val-Phe-Thr-NH₂; and
 H-D-Phe-Ala-Tyr-D-Trp-Lys-Val-Ala-β-D-Nal-NH₂.


- 5 If desired, one or more chemical moieties, e.g., a sugar derivative, mono or poly-hydroxy C₂₋₁₂ alkyl, mono or poly-hydroxy C₂₋₁₂ acyl groups, or a piperazine derivative, can be attached to the somatostatin agonist, e.g., to the N-terminus amino acid. See PCT Application WO 88/02756, European Application 0 329 295, and PCT Application No. WO 94/04752. An example of
 10 somatostatin agonists which contain N-terminal chemical substitutions are:



;




;



15

; and



- Processes for making polymer microspheres and/or nanospheres
 20 according to a method of the present invention are described herein. The examples are given for illustrative purposes and are not meant to limit the scope of the present invention. All references cited herein are incorporated herein by reference.

- Water solubility can be considerably diminished by co-precipitating the
 25 peptide as free base along with an inorganic bioresorbable matrix such as hydroxyapatite, calcium phosphate, alum, zinc hydroxide, etc. The presence of the inorganic bioresorbable matrix stabilizes the free, neutralized peptide by a combination of phenomena such as complexation, adsorption and the like.

The water insoluble peptide in the neutralized and adsorbed form can be prepared by dissolving a water soluble salt of a peptide such as acetate, trifluoroacetate, hydrochloride, sulphate, and the like, in a minimum amount of water and suspending hydroxyapatite in the solution, followed by addition of a weak base such as NaHCO_3 , triethylamine, and the like to bring the pH up to 7-8. The precipitate so formed is filtered, suspended in water and lyophilized.

Another method of decreasing the water solubility of the peptide is by the formation of salts or complexes with either mono- or multi- functional, monomeric or polymeric counterions, such as dodecylsulfate, bisphosphonates, phosphatidyl inisitol, phosphorylated, sulfated or carboxylated cyclodextrins, alginates, carboxymethyl cellulose, dioctylsulfosuccinates, tannates, anionically functionalized polyesters, polycarbonates, polyesters, polyanhydrides, polyethers, polyorthoesters, present as their copolymers or blends, and the anionic functionality may be carboxylate, phosphate or sulfate, and the like. The nature of an anionic group present in the counter-ion complex influences the water solubility of a peptide by displacing the equilibrium between the complexed and uncomplexed peptide. This equilibrium constant depends on the acidity of the anionic functionality which decreases in order sulphate> phosphate> carboxylate.

Water insoluble peptide salts or complexes of the present invention may be prepared by adding an equivalent amount of a salt containing the desired counterion, such as sodium dodecylsulfate, sodium tannate, sodium pamoate, sodium dioctylsulfosuccinate, sodium alginate, sodium cyclodextrin sulfate, sodium cyclodextrin phosphate and the like, in water to an aqueous peptide solution. The precipitated peptide complex is centrifuged, collected and suspended in water and lyophilized.

Polymers that can be used to form microspheres include biodegradable polymers such as polyesters (ex. polylactides, polyglycolides, polycaprolactone and copolymers and blends thereof) polycarbonates, polyorthoesters, polyacetals, polyanhydrides, their copolymers or blends, and non-biodegradable polymers such as polyacrylates, polystyrenes, polyvinylacetates, etc. The biodegradable polymers are intended to degrade under physiological conditions over a period of time, to yield natural metabolites, such that the implant or the

depot does not require to be retrieved once the drug is exhausted. These polymers may optionally contain anionic or cationic groups. The anionic groups present in the polymer may be sulphate, phosphate, or carboxylate, capable of forming salts with basic bioactive substances. The polymers can be endowed
5 with cationic functionalities (or basic groups), such as amino, amidino, guadino, ammonium, cyclic amino groups and nucleic acid bases, which can form salts with acidic bioactive molecules. In general a polymer solution can be prepared in a water immiscible organic solvent, containing between 1% and 20% polymer, preferably between 5% and 15%.

10 The polymer solution can be prepared in water immiscible organic solvents such as dichloromethane (DCM), chloroform, dichloroethane, trichloroethane, cyclohexane, benzene, toluene, ethyl acetate, and the like, which can be used alone or as a mixture thereof.

The polymer microspheres of the invention are made by either
15 suspending or dissolving the coprecipitates, salts or complexes in a polymer solution, and emulsifying this mixture/solution in aqueous medium containing a surfactant.

Emulsification of the oil droplets in aqueous medium is performed by known methods of dispersion. The dispersion methods include the use of mixers
20 such as propeller mixer, turbine mixer, colloid mill method, the homogenizer method, and the ultrasonic irradiation method.

The emulsification of the organic layer is done in an aqueous layer containing an emulsifier, which can stabilize O/W emulsions, such as anionic surfactants (sodium oleate, sodium stearate, sodium laurylsulphate, and the
25 like), non-ionic surfactants such as poly(oxyethylene) sorbitan fatty acid esters like Tween 20®, Tween 60®, Tween 80®, polyvinylpyrrolidone, polyvinyl alcohol, carboxymethyl cellulose, lecithin, gelatin, hyaluronic acid and the like, which may be used separately or in combination. The amount used may be chosen appropriately from a range of about 0.01% to 20%, preferably about
30 0.05% to 10%.

One important aspect of the present invention is the role of the pH of the aqueous surfactant medium in which the emulsion droplets are formed, in

partitioning the peptide into the aqueous medium, thereby reducing the encapsulation efficiency. Encapsulation efficiency is the amount of peptide actually present in the microspheres compared to the amount initially used in the process. The peptide loss to the aqueous medium can be minimized by
5 maintaining the pH of the aqueous medium between 6-8, preferably around 7.

Removal of the solvent in the oil phase is performed by any method known in the art: solvent removal may be effected by gradual reduction of pressure by stirring with a propeller type stirrer or a magnetic stirrer, or by adjusting the degree of vacuum with a rotary evaporator.

10 Microspheres and/or nanospheres formed by the removal of the solvent are collected by centrifugation or by filtration, followed by several repetitions of washing with deionized water to remove emulsifier and any unencapsulated peptide.

15 The washed microspheres are collected by filtration and dried under vacuum at about 30° C for about 24-48 hrs., in order to remove the residual solvent.

20 The peptide content of a microspheres and/or nanospheres made according to a process of this was determined by nitrogen analysis and also by HPLC method. In the HPLC method, about 20 mg of the sample dissolved in 0.1% TFA solution, was analyzed using a C₁₈ column, using eluants A (0.1% TFA) and eluant B (80% acetonitrile, 0.1% TFA), programmed at a gradient of 20% to 80% B in 50 min, and the peptide was monitored at 280nm by a UV detector (Applied Biosystems, Model # 785A). The HPLC system consisted of two Waters 510 pumps, Waters automated gradient controller and a Waters 712
25 wisp (Waters, Milford, MA).

Example 1

1(a): Preparation of neutralized Tryptorelin in presence of hydroxylapatite

200 mg of Hydroxyapatite (HAP) (American International Chemical, Natick, MA having particle size 2 µm) was suspended in water. 100 mg of the
30 acetate salt of pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂ (Tryptorelin, Kinerton, Dublin, Ireland) was dissolved in 1 ml of water and this solution was added to the suspension of HAP. The pH of the slurry was brought to about 7-8

29-08-2000

PCT/US99/14869

DESC

ART 34 AMDT

WO 00/04916

-18-

PCT/US99/14869

by adding 1N NaHCO₃ dropwise. The precipitate was left stirring for about 2 hrs. The precipitate was collected by centrifugation. The precipitate was suspended in water and lyophilized.

Peptide content by nitrogen analysis = 23.6% and by HPLC= 22.1%.

5 1(b): Preparation of neutralized polyvinyl alcohol (PVA) solution

Commercially available PVA has pH lower than 5, due to the presence of hydrolysis product of poly(vinylacetate) from which PVA is prepared. The PVA solution was cleaned by preparing a concentrated solution in water, neutralizing with NaHCO₃ solution, dialyzing against de-ionized water. The neutralized PVA
10 was precipitated in acetone, filtered and vacuum dried.

1(c): Preparation of p(di-lactic acid) microspheres

1 g of p(di-lactic acid) available from (Pharma-Biotech, ZI de Signes, BP 707, 83030 Toulon Cedex-9, France) (Mn= 32K, Mw= 54.4K) was dissolved in 10 ml DCM and 100 mg of the example 1(a) was suspended in the solution.
15 The solution was cooled in an ice-bath and was dispersed in 100 ml of 1% pre-cooled PVA (polyvinyl alcohol) solution using a Polytron homogenizer (Kinematica, Switzerland). DCM was rotovaped and the microspheres were collected by centrifugation. The particles were suspended in water and lyophilized. Peptide content determined by nitrogen analysis was 2% (calculated
20 2.2%).

1(d): Preparation of neutralized Tryptorelin in presence of HAP

To 500 mg of acetate salt of pyroGlu-His-Trp-Ser-Tyr-DTrp-Leu-Arg-Pro-Gly-NH₂ (Kinterton, Dublin, Ireland) dissolved in 5 ml of water was added 200 mg of HAP. The pH of the solution was brought up to 7-8 using 1N NaHCO₃. The
25 solution was left standing for about 2 hrs. and the precipitate was collected by centrifugation, and suspended in water and lyophilized. Peptide content by nitrogen analysis = 58.9%.

1(e): Preparation of microspheres containing 1(d)

Microspheres were prepared by employing the same procedure as 1(b).
30 Peptide content 4.9%.

1(f): Co-precipitation of Tryptorelin and Calcium Phosphate monobasic

A solution of 100 mg of CaHPO₄ (Aldrich Chemicals, St. Louis, MO) and 100 mg of the acetate salt of pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-

29-08-2000

PCT/US99/14869

DESC

ART 34 AMDT

WO 00/04916

-19-

PCT/US99/14869

NH₂ (Kinenton, Dublin, Ireland) in water was prepared. The pH of the solution was brought to about 7 using 1N NaHCO₃ and left for about 24 hrs. for the completion of the precipitate. The precipitate was centrifuged, collected, suspended in water and lyophilized. Peptide content determined by HPLC method was 49.4%.

1(g): In-Vivo testing of 1(c) and 1(e) in rats

Formulations 1(c) & 1(e) were administered in male rats by IM injection at a dose of 300 µg of tryptorelin equivalent per rat, as a dispersion of the microspheres in 1% (w/v) Tween 20® (Aldrich Chemicals, St. Louis, MO) and 2% (w/v) carboxymethyl cellulose (Aldrich Chemicals, St. Louis, MO). The testosterone response was monitored by RIA: 50µL of the blood sample, 200µL of 125I-testosterone and 200µL of antiserum were poured into tubes which were shaken and incubated for 2 hrs. at 37°C. The immunoprecipitant reagent (1ml) was added to each tube and all the tubes were incubated for 15 minutes at room temperature. The supernatant was eliminated after centrifugation and the radioactivity was measured with LKB Wallace gamma counter. The plasma testosterone levels are shown below.

Table 1

Plasma testosterone response (ng/ml) to IM injection of 300 µg of Tryptorelin equivalent/rat

Sample	6 h	Day 2	Day 3	Day 5	Day 10	Day 15	Day 23	Day 30	Day 37
1(c)	5.37	4.09	0.74	0.45	0.30	0.31	0.90	0.61	0.81
1(e)	5.32	3.58	1.04	0.29	0.38	0.56	0.80	0.75	0.72

Example 22(a): Preparation of water-insoluble salts of peptides with carboxylated PLGA

Water insoluble salts of peptides with carboxy functionalized PLGA were prepared as described in US Patent No. 5,672,659 the teachings of which are incorporated herein by reference.

AMENDED SHEET

In a typical experiment 4 g of p(dl-lactide-co-glycolide) having Mn= 5560 and Mw= 12200, acid and polymer composition 70/30 dl-lactide/glycolide, prepared using 2% malic acid was dissolved in acetone. 0.73 ml 1N NaHCO₃ was added and stirred. The acetate salt of pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂ (Kinerton, Dublin, Ireland) (0.64g) was dissolved in 2 ml water and was added to the polymer solution. The solution was stirred for about 2 hrs and precipitated in 400 ml cold water kept at about 4-6° C. Peptide content determined by nitrogen analysis was 9.8%.

2(b): Preparation of microspheres of 2(a)

1.5 g of the above vacuum dried complex was dissolved in 15 ml of DCM. The DCM solution was cooled in an ice-bath along with 150 ml of 1% PVA solution prepared from pure PVA as described above in Example 1(b). The DCM solution was slowly added to the PVA solution while it was being dispersed using a Polytron Homogenizer. The DCM was evaporated off, and the microspheres were collected by centrifugation. The microspheres were suspended in water and lyophilized. Peptide content by nitrogen analysis was 8.4%.

2(c): Preparation of dioctylsulfosuccinate of a Somatostatin analogue

To 100 mg of the somatostatin analogue [4-(2-hydroxyethyl)-1-piperazinylacetyl-D-cyclo(Cys-Tyr-D-Trp-Lys-Abu-Cys)-Thr-NH₂ acetate (Kinerton, Dublin, Ireland) dissolved in 3 ml of water was added 80 mg of sodium dioctylsulfosuccinate (Aldrich Chemicals, St. Louis, MO) dissolved in 4 ml of water. The precipitated peptide salt was collected by centrifugation, suspended in water and lyophilized. Peptide content by nitrogen analysis= 47.3%.

2(d): Preparation of p(dl-LGA) microspheres containing dioctylsulfosuccinate of a Somatostatin analogue

1 g p(dl-LA) was dissolved in 10 ml DCM. 150 mg of the [4-(2-hydroxyethyl)-1-piperazinylacetyl-D-cyclo(Cys-Tyr-D-Trp-Lys-Abu-Cys)-Thr-NH₂ (Kinerton, Dublin, Ireland) dioctylsulfosuccinate salt prepared in example 2(c) was added to the polymer solution. The mixture was sonicated to obtain a solution. This solution was cooled in an ice-bath, and was added to a pre-cooled 1% neutralized PVA solution, having pH=7, under stirring using a Polytron

Homogenizer. DCM was rotovaped off. Microparticles were filtered, washed with water, and dried under vacuum. Nitrogen analysis gave a peptide content of 7%.

2(e): In-vivo testing of 2(b) in rats

Formulation 2(b) was administered in male rats by IM injection at a dose
5 of 300 µg of tryptorelin per rat, as a dispersion of the microspheres in 1% (w/v) Tween 20® and 2% (w/v) carboxymethyl cellulose. The testosterone response was monitored by RIA as described hereinabove. The plasma testosterone levels are shown below in Table 2.

Table 2

10 Plasma testosterone response (ng/ml) to IM injection of 300 µg of tryptorelin equivalent/rat.

Sample	Day 2	Day 5	Day 10	Day 15	Day 26	Day 36	Day 46
2(b)	3.98	1.04	0.63	0.76	0.60	0.37	0.86

CLAIMS

What is claimed is:



1. A process for preparing polymer microspheres comprising a polymer and a peptide, which comprises the steps of:
 - 5 neutralizing a peptide salt with a weak base in an aqueous medium wherein said medium comprises a suspension of hydroxyapatite or a solution of calcium mono-hydrogen phosphate to form a precipitate;
 - isolating the precipitate;
 - suspending the precipitate in an organic solvent, which comprises a
 - 10 polymer dissolved therein to form a suspension;
 - dispersing the suspension in an aqueous solution of a surfactant; and
 - evaporating the organic solvent to isolate the polymer microspheres.
2. A process according to claim 1, comprising the additional step of dissolving the peptide salt in a minimum of water before neutralizing the peptide
- 15 salt.
3. A process according to claim 2, wherein the surfactant is one or more of sodium oleate, sodium stearate, sodium laurylsulphate, a poly(oxyethylene) sorbitan fatty acid ester, polyvinylpyrrolidone, polyvinyl alcohol, carboxymethyl cellulose, lecithin, gelatin or hyaluronic acid.
- 20 4. A process according to claim 3, wherein the surfactant is polyvinyl alcohol and the pH of the polyvinyl alcohol is 6.5-7.5.
5. A process according to claim 4, wherein the pH of the polyvinyl alcohol is 6.9-7.1.
6. A process according to claim 5, wherein the organic solvent is
- 25 dichloromethane, chloroform or ethyl acetate.
7. A process according to claim 6, wherein the organic solvent is dichloromethane and the concentration of the polymer in the organic solvent is 0.5% to 30% by weight.
8. A process according to claim 7, wherein the concentration of the
- 30 polymer in dichloromethane is 0.5% to 10% by weight.
9. A process according to claim 8, wherein the peptide is growth hormone releasing peptide, luteinizing hormone-releasing hormone, somatostatin, bombesin, gastrin releasing peptide, calcitonin, bradykinin,

galanin, melanocyte stimulating hormone, growth hormone releasing factor, amylin, tachykinins, secretin, parathyroid hormone, enkephalin, endothelin, calcitonin gene releasing peptide, neuromedins, parathyroid hormone related protein, glucagon, neurotensin, adrenocorticotrophic hormone, peptide YY, glucagon releasing peptide, vasoactive intestinal peptide, pituitary adenylate cyclase activating peptide, motilin, substance P, neuropeptide Y, or TSH or an analogue or a fragment thereof or a pharmaceutically acceptable salt thereof.

10. A process according to claim 9, wherein the peptide is the LHRH analogue of the formula pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂.

11. A process according to claim 10, wherein the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

12. A process according to claim 9, wherein the peptide is selected from the group of somatostatin analogues consisting of H-D-β-Nal-Cys-Tyr-D-Trp-Lys-Thr-Cys-Thr-NH₂,



13. A process according to claim 12, wherein the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

14. A polymer microsphere made according to the process of claim 1.

15. A polymer microsphere made according to the process of claim

11.

16. A polymer microsphere made according to the process of claim

13

17. A process for preparing polymer microspheres and nanospheres comprising a polymer and a peptide, which comprises the steps of:

dissolving a salt of a peptide complexed with an anionically or cationically functionalized biodegradable polyester in an organic solvent to form a solution; dispersing the solution in an aqueous solution of a surfactant; and evaporating the organic solvent to isolate the polymer microspheres and nanospheres.

18. A process according to claim 17, wherein the anionically functionalized biodegradable polyester is functionalized with an anionic moiety selected from the group consisting of carboxylate, phosphate and sulfate and the cationically functionalized biodegradable polyester is functionalized with a cationic moiety selected from the group consisting of amino, amidino, guadino, ammonium, cyclic amino groups and nucleic acid bases.

19. A process according to claim 18 wherein the organic solvent is dichloromethane, chloroform or ethyl acetate.

20. A process according to claim 19, wherein the organic solvent is dichloromethane and the concentration of the polymer in the dichloromethane is 0.5% to 30% by weight.

21. A process according to claim 20, wherein the concentration of the polymer in the dichloromethane is 0.5% to 10% by weight.

22. A process according to claim 21, wherein the surfactant is one or more of sodium oleate, sodium stearate, sodium laurylsulphate, a poly(oxyethylene) sorbitan fatty acid ester, polyvinylpyrrolidine, polyvinyl alcohol, carboxymethyl cellulose, lecithin, gelatin or hyaluronic acid.

23. A process according to claim 22, wherein the surfactant is polyvinyl alcohol and the pH of polyvinyl alcohol is 6.5-7.5.

24. A process according to claim 23, wherein the pH of polyvinyl alcohol is 6.9-7.1.


25. A process according to claim 24, wherein the peptide is growth hormone releasing peptide, luteinizing hormone-releasing hormone, somatostatin, bombesin, gastrin releasing peptide, calcitonin, bradykinin, galanin, melanocyte stimulating hormone, growth hormone releasing factor, amylin, tachykinins, secretin, parathyroid hormone, enkephalin, endothelin, calcitonin gene releasing peptide, neuromedins, parathyroid hormone related protein, glucagon, neurotensin, adrenocorticotrophic hormone, peptide YY,

glucagon releasing peptide, vasoactive intestinal peptide, pituitary adenylate cyclase activating peptide, motilin, substance P, neuropeptide Y, or TSH or an analogue or a fragment thereof or a pharmaceutically acceptable salt thereof.


26. A process according to claim 25, wherein the peptide is the LHRH
5 analogue of the formula pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂.

27. A process according to claim 26, wherein the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

28. A process according to claim 25, wherein the peptide is selected
10 from the group of somatostatin analogues consisting of H-D-β-Nal-Cys-Tyr-D-Trp-Lys-Thr-Cys-Thr-NH₂,



, and



15 .

29. A process according to claim 28, wherein the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

30. A polymer microsphere made according to the process of claim
20 17.

31. A polymer microsphere made according to the process of claim
27.

32. A polymer microsphere made according to the process of claim
29.

25 33. A process for preparing polymer microspheres and nanospheres comprising a polymer and a peptide, which comprises the steps of:

dissolving a salt of a peptide complexed with an anionic counterion in an organic solvent which is selected from the group consisting of dichloromethane, chloroform and ethyl acetate to form a solution;

30 dispersing the solution in a surfactant; and

evaporating the organic solvent to isolate the polymer microspheres and nanospheres.

34. A process according to claim 33, wherein the anionic counterion is dioctylsulfosuccinate, dodecylsulfate, tannate, pamoate, alginate, cyclodextrin sulfate, cyclodextrin phosphate, bisphosphonate or inositol phosphate.

35. A process according to claim 34 wherein the organic solvent is dichloromethane.

36. A process according to claim 35, wherein the concentration of the polymer in dichloromethane is 0.5% to 30% by weight.

37. A process according to claim 36, wherein the concentration of the polymer in dichloromethane is 0.5% to 10% by weight.

38. A process according to claim 37, wherein the surfactant is one or more of sodium oleate, sodium stearate, sodium laurylsulphate, a poly(oxyethylene) sorbitan fatty acid ester, polyvinylpyrrolidone, polyvinyl alcohol, carboxymethyl cellulose, lecithin, gelatin or hyaluronic acid.

39. A process according to claim 38, wherein the surfactant is polyvinyl alcohol and the pH of polyvinyl alcohol is 6.5-7.5.


40. A process according to claim 39, wherein the pH of polyvinyl alcohol is 6.9-7.1.

41. A process according to claim 40, wherein the peptide is growth hormone releasing peptide, luteinizing hormone-releasing hormone, somatostatin, bombesin, gastrin releasing peptide, calcitonin, bradykinin, galanin, melanocyte stimulating hormone, growth hormone releasing factor, amylin, tachykinins, secretin, parathyroid hormone, enkephalin, endothelin, calcitonin gene releasing peptide, neuromedins, parathyroid hormone related protein, glucagon, neurotensin, adrenocorticotrophic hormone, peptide YY, glucagon releasing peptide, vasoactive intestinal peptide, pituitary adenylate cyclase activating peptide, motilin, substance P, neuropeptide Y, or TSH or an analogue or a fragment thereof or a pharmaceutically acceptable salt thereof.


42. A process according to claim 41, wherein the peptide is the LHRH analogue of the formula pyroGlu-His-Trp-Ser-Tyr-D-Trp-Leu-Arg-Pro-Gly-NH₂.

43. A process according to claim 42, wherein the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

44. A process according to claim 41, wherein the peptide is selected
5 from the group of somatostatin analogues consisting of H-D- β -Nal-Cys-Tyr-D-Trp-Lys-Thr-Cys-Thr-NH₂,



, and



10 .

45. A process according to claim 44, wherein the polymer is polylactide-co-glycolide, polycaprolactone or polyanhydride or a copolymer or blends thereof.

46. A polymer microsphere made according to the process of claim
15 33.

47. A polymer microsphere made according to the process of claim
43.

48. A polymer microsphere made according to the process of claim
45.

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US 99/14869 SAE 242610

In diesem Anhang sind die Mitglieder
der Patentfamilien der im obenge-
nannten internationalen Recherchenbericht
angeführten Patentedokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visé ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

In Recherchenbericht angeführtes Patentedokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A	5445632	29-08-1995	
		AT A	1489/92
		AT B	403348
		AU A1	20436/92
		AU A1	20437/92
		AU B2	651711
		AU B2	652844
		BE AD	1005696
		BE AF	1005697
		BR A	9205375
		CA AA	2074320
		CA AA	2074322
		CA C	2074320
		CH A	683149
		CH A	683592
		CH A	1070344
		CN A3	9300660
		DE A1	4233282
		DE A1	4233284
		DE C2	4233284
		DE U1	9319084
		DK A0	938/92
		DK A0	938/92
		DK A	938/92
		DK A	938/92
		ES AA	2037621
		ES BA	2037621
		ES AA	2050070
		ES BA	2050070
		FI A0	923320
		FI A0	923321
		FI A	923320
		FI A	923321
		FR A1	2679450
		FR A1	2680109
		FR B1	2680109
		FR B1	2679450
		GB A0	9215479
		GB A0	9215480
		GB A1	2257909
		GB A1	2257973
		GB B2	2257909
		GB B2	2257973
		GR A	92100323
		GR B	1001446
		GR B	1002548
		HR A1	9202229
		HU A0	9301186
		HU A2	64234
		IE B	69567
		IE B	71199
		IL A0	102590
		IL A0	102591
		IL A1	102591
		IL A1	102590
		IT A0	920093
		IT A	1239891
		IT A	1239892
		JP A2	5221855
		JP A2	6172208
		JP B2	2842736
		LU A	88150
		LU A	88151
		MX A1	9204268
		NL A	9201309
		NL A	9201310
		NO A0	9228885
		NO A0	9228886
		NO A	9228885
		NO A	9228886
		NO B1	304057
		NO B1	304136
		NO A	324444
			15-06-1997
			26-01-1998
			28-01-1993
			28-01-1993
			28-07-1994
			08-09-1994
			21-12-1993
			21-12-1993
			08-03-1994
			23-01-1994
			23-01-1994
			08-04-1999
			31-01-1994
			15-04-1994
			31-03-1993
			19-01-1994
			28-01-1994
			28-01-1993
			31-07-1997
			04-11-1997
			21-07-1993
			21-07-1993
			23-01-1993
			23-01-1993
			21-07-1993
			21-07-1993
			23-01-1993
			16-06-1994
			01-02-1994
			01-05-1994
			01-10-1994
			21-07-1993
			21-07-1993
			23-01-1993
			23-01-1993
			12-02-1993
			02-09-1994
			08-06-1995
			02-09-1993
			02-09-1993
			27-01-1994
			27-01-1993
			10-01-1996
			28-02-1996
			24-05-1996
			30-12-1993
			28-01-1997
			30-04-1996
			28-07-1996
			28-12-1993
			16-10-1996
			12-02-1993
			14-01-1993
			14-01-1993
			10-06-1997
			13-07-1997
			21-07-1993
			28-03-1996
			28-03-1996
			31-03-1993
			21-06-1994
			06-01-1999
			15-03-1993
			15-03-1993
			31-03-1994
			14-02-1993
			16-02-1993
			21-07-1993
			25-01-1993
			25-01-1993
			19-10-1993
			02-11-1993
			04-10-1993

			FL A1	298504	10-01-1994
			PL B1	169387	31-07-1996
			PT A	100713	31-08-1993
			PT A	100712	28-10-1993
			PT E	100712	30-07-1993
			PT E	100712	30-07-1993
			SE AC	9202212	21-07-1993
			SE AC	9202213	21-07-1993
			SE A	9202212	23-01-1993
			SE A	9202213	23-01-1993
			SE A	9200152	31-03-1993
			US A	5637568	10-06-1997
			WD A1	9201802	04-02-1993
			WD A	9205425	28-04-1993
			WD A	9205486	28-04-1993
JP A2	4036233	06-02-1992	keine - none - rien		
US A	5160745	03-11-1992	AT E	132035	15-01-1996
			AU A1	72668787	19-11-1987
			AU B2	600723	23-08-1990
			CA A1	1309457	03-11-1992
			DE CO	3751647	08-02-1996
			DE T2	3751647	20-06-1996
			DE AC	2446787	14-05-1987
			DE A	2446787	17-11-1987
			EP A2	245820	19-11-1987
			EP A3	245820	30-01-1991
			EP B1	245820	27-12-1995
			ES T2	2080715	16-02-1996
			GR T2	3018872	31-05-1996
			JP A2	63028445	06-02-1988
			JP B2	2634813	30-07-1997
			NZ A	220322	26-04-1991
			US A	4741872	03-05-1988
US A	5578709	23-11-1996	AT E	163230	15-02-1998
			AU A1	63585794	26-09-1994
			CA AA	63157793	15-09-1994
			DE CO	64408527	19-03-1998
			DE T2	64408527	04-06-1998
			EP A1	688429	27-12-1995
			EP A1	809110	26-11-1997
			EP B1	688429	11-02-1998
			ES T2	2113094	16-04-1998
			JP T2	9507806	20-08-1996
			WD A	9420856	15-09-1994
			US A	5454294	16-01-1996
			US A	5554730	10-06-1996
			US A	5849884	15-12-1998
			WD A2	9620012	04-07-1996
			WD A3	9620012	13-02-1997

COMBINED DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled **ENCAPSULATION OF WATER SOLUBLE PEPTIDES**, the specification of which:

- ☐ is attached hereto.
☒ was filed on January 23, 2001 as Application Serial No. 09/744,350 and was amended on _____
☒ was described and claimed in PCT International Application No. PCT/US99/14869 filed on July 9, 1999 and as amended under PCT Article 19 on _____.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose all information I know to be material to patentability in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim the benefit under Title 35, United States Code, §119(e)(1) of any United States provisional application(s) listed below:

U.S. Serial No.	Filing Date	Status
60/093,914	July 23, 1998	Expired

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose all information I know to be material to patentability as defined in Title 37, Code of Federal Regulations, §1.56(a) which became available between the filing date of the prior application and the national or PCT international filing date of this application:

U.S. Serial No.	Filing Date	Status
09/121,653	July 23, 1998	Abandoned

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

Country	Application No.	Filing Date	Priority Claimed
			<input type="checkbox"/> Yes <input type="checkbox"/> No
			<input type="checkbox"/> Yes <input type="checkbox"/> No

Combined Declaration and Power of Attorney

Page 2 of 2 Pages

I hereby appoint the following attorneys and/or agents to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

6- Y. Rocky Tsao, Reg. No. 34,053; Brian R. Morrill Reg. No. 42,098; Alan F. Feeney Reg. No. 43,609; Timothy A. French, Reg. No. 30,175; Eric L. Pahl, Reg. No. 32,590; and Frank R. Occhuiti, Reg. No. 35,306.

Address all telephone calls to Brian R. Morrill at telephone number (508) 478-0144.

Address all correspondence to Brian R. Morrill, Esq. at:

Biomeasure, Incorporated
27 Maple Street
Milford, MA 01757

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patents issued thereon.

100 Full Name of Inventor: FRANCIS X. IGNATIUS

Inventor's Signature: _____

Date: 5-7-2001

Residence Address: Exton, Pennsylvania PA

Citizenship: IN

Post Office Address: 606 Sylvania Road
Exton, Pennsylvania 19341
United States of America